7F, No. 349, Sec. 2, Renhe Road, Dashi, Taoyuan, Taiwan (R.O.C) 335

Cat No.: 7-1S-1000-046

Revision:

# AllnGaP LED DICE

## Part NO.: AOC-112YxA Series

#### **Features**


- Yellow Color Emission
- Excellent performance and high efficiency
- Great reliability even in harsh environment

### **Description**

AOC-112YxA series is a yellow color emitting AlInGaP LED grown by MOCVD technique. Its structure enables enhanced quantum efficiency and therefore a greater light intensity. This device is designed to suit the growing demand in the compact size electronic goods.

#### **Chip Dimensions**





Chip Size: 10.8mil×10.8mil±0.5mil Bonding Pad: \$\phi4.0\text{mil}\pm0.4\text{mil}\$ Chip Thickness: 6.5mil±1.0mil

N-electrode

#### **Specification and Optical Characteristics**

Measuring Item	Symbol	Condition	Min	Тур	Max	Unit
Forward Voltage	$V_{\mathrm{F}}$	I <sub>F</sub> =20mA	1.70	-	2.20	V
Reverse Current	Ir	V <sub>R</sub> =-5V	-	-	1.0	$\mu$ A
Dominant Wavelength	λd	I <sub>F</sub> =20mA	582	-	598	nm
Max. Junction Temperature	$T_{\text{max}}$	-	≦ 115			$^{\circ}\!\mathbb{C}$
Max. DC forward current	$I_{\mathrm{f}}$	$Ta = 25^{\circ}C$	≦ 50			mA
Max. pulse forward current	$ m I_{fm}$	Ta = 25°C	≦ 100			mA
(Pulse width 0.1 msec, frequency=1 kHz.)	1 fm	1 <b>u</b> 25 0				
Storage temperature	$T_{\text{stg}}$	Chip on tape	0 ~ 40			$^{\circ}$ C
Storage temperature		Only chip	<b>-</b> 40 ~ 80			

# Available Dominate Wavelength and Iv Matrix

Minimum Intensity	IV≥	IV≥	IV≥	IV≥	IV≥	IV≥	IV≥	IV≥	IV≥
(@20mA)	90mcd	100mcd	110mcd	120mcd	130mcd	140mcd	150mcd	160mcd	170mcd
Grade	Н	I	J	K	L	M	N	О	P

- All measurements are done with AOC's standard testing equipment.
- Luminance intensity is measured on bare chip.
- Above contents are subject to change without notice. Special requests are also welcome, please contact AOC's sale representative for any request. YxA represents anyone of YSA(582nm-592nm) and YLA(590nm-598nm).